

## GARNET SPECIFICATIONS

GRADE: # 50-80

### MINERAL COMPOSITION

MINERALS	Standard (%)
GARNET	MIN 97 %
ILMENITE	< 2 %
MONAZITE	< 0.25 %
OTHERS	< 0.60 %

### PHYSICAL CHARACTERISTICS

Test Parameter	Standard	Typical (%)
Conductivity	Max 250 $\mu\text{s}/\text{cm}$	105 $\mu\text{s}/\text{cm}$ at 25.5°C
Chloride	Max 25 PPM	18 PPM
Hardness	Min 7 Moh Scale	7 Moh Scale
Moisture	Max 0.20%	0.12%
Total Suspended Solids	Max 2000 mg/l	1620 mg/l
Bulk Density	2.20 - 2.40 $\text{g}/\text{cm}^3$	2.32 $\text{g}/\text{cm}^3$

### CHEMICAL COMPOSITION

Elements	Standard (%)	Typical (%)
SiO <sub>2</sub>	33.0 - 37.0 %	35.82
Al <sub>2</sub> O <sub>3</sub>	19.0 - 22.0%	21.25
Fe <sub>2</sub> O <sub>3</sub>	31.0 - 37.0%	36.10
MgO	3.0 - 8.0 %	3.04
CaO	1.0 - 3.0 %	2.32
TiO <sub>2</sub>	0.20 - 2.0 %	1.16

### SIEVE ANALYSIS

Microns (MM)	Mesh	Standard (%)
0.425	+40	0.01 - 0.50
0.300	+50	0.5 - 5
0.250	+60	35 - 45
0.180	+80	40 - 50
0.150	+100	5 -10
PAN		0.5 - 2

Note: Garnet is a natural product. Variations in the grain size occur from time to time.

The grain size distributions can be expected within the above ranges.

### Maxworth Minerals India Pvt. Ltd.

Plot No. I, Phase II, Visakhapatnam Special Economic Zone, Duvvada, Visakhapatnam – 530046

Head Office: 37/1989, Bhattathiripad Road, Off Kaloor - Kadavanthara Road, Kaloor, Kochi - 682017, Kerala, India.